

ZINC GUARD COLD GALVANISING COATING

Features & Benefits

- A zinc rich, heavy duty corrosion inhibitive primer
- Suitable for use on steel, wrought iron and galvanised iron
- Contains 91% zinc in dry film

Zinc Guard Cold Galvanising Coating (Brush On)

Cold Galvanising Coating	500m l	230731050
Cold Galvanising Coating	1 L	230731100
Cold Galvanising Coating	4L	230731400

Zinc Guard Cold Galvanising Coating (Horizontal Spray)

Cold Galvanising Coating	230732006



Suitable Surfaces

Steel, wrought iron & galvanised iron



Coverage Aerosol Spray

Approximately 2 sqm per aerosol can (depending on the surface)

Brush On

Approximately 6-8 sqm per litre



Drying Time

Touch dry in 20 minutes. Recoat after 3-4 hours. Dry to handle (hard dry) in 16-24 hours.



Ideal Application TemperatureBetween 10°C and 35°C

