

## **CABAC CAST RESIN JOINT DATA SHEET - GTA Series Low Voltage Cast Resin Straight Through Joints**




Table 1. shows gel time and complete solidifying time (shown in minutes) curves for installation reference at variable temperatures.


echnical Data	Value	According to DIN VDE 0291	
ot life @			
°C	35 min		
3°C	20 min	product conforms ±30%	
5℃	15 min		
Reactant	20000	- 80	
pen cup flash point	>200°C	>55	
ensile strength	≥8.0 Mpa	≥5.0	
lot aging	-5 Shore A	-7	
dhesive	>1500 CP. S	<1500	
ear elongation	≥100%	≥50	
Gel time for 300 ml @	23℃		
Pouch >1000ml	26 min	product conforms ±10%	
Pouch <1000ml	17 min	product conforms ±10%	
Max. reaction temp	60°C/333K	product conforms ±10%	
otal vol. variable when hardening	6%	max. 6.5%	
Cast resin component		722	
pen cup flash point	>200°C	>100	
Pensity	1.07g/cm <sup>3</sup>	-	
mpact strength	$>10kJ/m^2$	> 10kJ/m²	
lardness	75 Shore A	min. 20 Shore D	

Legend Corporate Services Pty Ltd ABN 81 006 722 2292 8 Distribution Place, Seven Hills NSW 2147

PO Box 72, Seven Hills NSW 2147

Administration T+61 2 9678 5000 F+61 2 9678 5070





**Table 2**. shows hardness levels (shore A) together with elapsed time in hours at variable temperatures.

time (a)				
Technical data	Value	According to DIN VDE 0291		
Expansion coefficient in temp				
range of 20-50°C	5.9 x 10-4 K <sup>-1</sup>	product conforms $\pm 15\%$		
Thermal conductivity	0.2W x m-1 x K <sup>-1</sup> product conforms ±20%			
Flammability	Class II c	ss II c acc to DIN VDE 0304, part		
Water absorption 42 days@50°C	360mg	max. 400 mg		
Electrolytic corrosion	A 1	-		
Voltage test@		no breakdown @ test voltage		
23℃	>20kV	20kV		
80℃	>10kV	20kV		
Dielectric dissipation factor				
@ 23℃ and 50Hz	0.08	max. 0.1		
@ 23℃ and 1kHz	0.05			
Relative permittivity				
23°C @ 50Hz	5	< 6		
23°C @ 1kHz	5.1	•		
Tracking resistance	KA 3c	min. KA 3c		
Physical values after 28 days of				
mmersion in 90°C water				
Tensile strength	8.2N/mm <sup>2</sup>	≥65% of initial value		
Elongation at break	60%	≥65% of initial value		
Hardness	47 Shore	≥80% of initial value		


**Legend Corporate Services Pty Ltd** ABN 81 006 722 2292 8 Distribution Place, Seven Hills NSW 2147 PO Box 72, Seven Hills NSW 2147

Administration T+61 2 9678 5000 F+61 2 9678 5070





Туре	Cable Size mm²	L(mm)	H(mm)	D1 (mm)	D2(mm)
GTA1	4 x 1.5 - 10	202	36	8	26
GTA3	4 x 10 - 25	260	47	16	32
GTA4	4 x 35 - 50	360	55	21	38
GTA5	4 x 50 - 70	400	70	26	41
GTA6	4 x 95 - 150	530	100	35	56
GTA7	4 x 185 - 300	700	125	47	74



**Legend Corporate Services Pty Ltd** ABN 81 006 722 2292 8 Distribution Place, Seven Hills NSW 2147 PO Box 72, Seven Hills NSW 2147

Administration T+61 2 9678 5000 F+61 2 9678 5070